

## CUTBACK BITUMEN MC-800 SPECIFICATIONS

Parameters	Min	Max	Test Method
<b>Kinematic viscosity at 60°C mm<sup>2</sup>/s</b>	800	1600	ASTM D2170
<b>Flash point (tag open-cup), °c</b>	66	-	ASTM D3143
<b>Distillate test: distillate, volume percent of total distillate at 360°C:</b>			
<b>To 225°C</b>	-	-	ASTM D402
<b>To 260°C</b>	-	40	ASTM D402
<b>To 316°C</b>	45	85	ASTM D402
<b>Residue from distillation to 360°C, percent volume by difference</b>	75	-	ASTM D402
<b>Test on residue from distillation:</b>			
<b>Penetration at 25°C</b>	120	250	ASTM D5
<b>Ductility at 25°C</b>	100	-	ASTM D113
<b>Solubility in trichloroethylene, %</b>	99	-	ASTM 2042
<b>Water, %</b>	-	0.2	ASTM D95