

CUTBACK BITUMEN MC-30 SPECIFICATIONS

Parameters	Min	Max	Test Method
Kinematic viscosity at 60°C mm²/s	30	60	ASTM D2170
Flash point (tag open-cup), °c	38	-	ASTM D3143
Distillate test: distillate, volume percent of total distillate at 360°C:			
To 225°C	-	35	ASTM D402
To 260°C	30	75	ASTM D402
To 316°C	75	93	ASTM D402
Residue from distillation to 360°C, percent volume by difference	50	-	ASTM D402
Test on residue from distillation:			
Penetration at 25°C	120	300	ASTM D5
Ductility at 25°C	100	-	ASTM D113
Solubility in trichloroethylene, %	99	-	ASTM 2042