

## CUTBACK BITUMEN RC-3000 SPECIFICATIONS

Parameters	Min	Max	Test Method
<b>Kinematic viscosity at 60°C mm<sup>2</sup>/s</b>	3000	6000	ASTM D2170
<b>Flash point (tag open-cup), °c</b>	27	-	ASTM D3143
<b>Distillate test: distillate, volume percent of total distillate at 360°C:</b>			
<b>To 190°C</b>	-	-	ASTM D402
<b>To 225°C</b>	-	-	ASTM D402
<b>To 260°C</b>	25	-	ASTM D402
<b>To 316°C</b>	70	-	ASTM D402
<b>Residue from distillation to 360°C, percent volume by difference</b>	80	-	ASTM D402
<b>Residue from distillation to 360°C:</b>			
<b>Viscosity at 60°C</b>	60	240	ASTM D5
<b>Penetration at 25°C</b>	80	120	ASTM D5
<b>Ductility at 25°C</b>	100	-	ASTM D113
<b>Solubility in trichloroethylene, %</b>	99	-	ASTM 2042