

SPECIFICATIONS OF OXIDIZED BITUMEN 90/10

Parameters	Test method	Unit	Specification
Specific gravity @ 25°C	ASTM D70	kg/cm ³	1.05 approx.
Penetration @ 25°C	ASTM D5	mm/10	5/15
Softening point °C	ASTM D36	°C	85/95
Ductility @25 °C	ASTM D113	cm	1.5
Loss on heating(wt) %	ASTM D6	wt %	0.2
Flashpoint °C	ASTM D92	°C	250
Solubility in CS₂(wt) %	ASTM D4	wt %	99.5
Spot test	A.A.S.H.O.T102	---	Negative